

# Elastever® E1190A

**Material Description:**

Elastever® E1190A is a unreinforced Thermoplastic Polyurethane Elastomer(TPU-polyether) product. Characteristics include:Cold Resistant,Environmental Protection.

**General**

Material Status	• Commercial: Active
Availability	• Asia Pacific
	• Europe
	• Middle East
Features	• Shock Absorption
	• Ageing Resistant
	• Good Processability
	• Oil Resistant
Appearance	• Natural Color
Forms	• Pellets
RoHS Compliance	• RoHS Compliant
Processing Method	• Injection Molding

Physical Properties	Typical Value	Unit	Test Method
Density/Specific Gravity	1.14	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.75	%	ASTM D955
Water Absorption (24 hr, 23°C)	0.3	%	ASTM D570

Hardness	Typical Value	Unit	Test Method
Durometer Hardness (Shore A)	90		ASTM D2240

Mechanical Properties	Typical Value	Unit	Test Method
Tensile Strength	47	MPa	ASTM D638
Tensile Elongation (Break)	12	%	ASTM D638
Flexural Modulus	72	MPa	ASTM D790

Processing Information	Typical Value	Unit
Rear Temperature	182 to 218	°C
Middle Temperature	182 to 218	°C
Front Temperature	182 to 218	°C
Mold Temperature	16 to 66	°C
Injection Pressure	68.9 to 103	MPa

Additional Information

Mold Shrinkage, Linear-Flow, ASTM D-955, 0.25in.: 15mil/in.

**CONTACT:**

CHINA/JIANG SU  
 江苏新孚达复合材料有限公司  
 NFD Composite Material (Jiangsu) Co., Ltd  
 Email:yanghui@nfdpla.com  
 Internet:www.nfdpla.com