

Matreial Data Sheet

技术数据表

NFD Composite Material (Jiangsu) Co., Ltd

Hepla® H7240GB

Material Description:

Hepla® H7240GB is a Polyamide 66 (Nylon 66) product filled with 40% glass bead. Characteristics include: Electrically Insulating, Weather Resistant, High Temperature Stiffness.

General			
Material Status	 Commercial: Active 		
Availability	Asia Pacific		North America
	Europe		Latin America
	Middle East		Africa
Filler/Reinforcement	Glass Bead, 40% Filler by W	/eight	
Features	Creep Resistant	<u> </u>	Hot Water Moldability
	Electrically Insulating		Low CLTE
	Fatique Resistant		Low Shrinkage
	High Impact Resistance		Low Warpage
	Heat Resistant		Weather Resistant
	High Temperature Stiffness		
Applications	Aircraft Applications		Consumer Applications
	Automotive Applications		Industrial Applications
RoHS Compliance	Contact Manufacturer		maderial ripplications
Processing Method	Injection Molding		
	jeeden melang		
Physical Properties	Typical Value	Uniț	Test Metho
Specific Gravity	1.44	g/cm ³	ASTM D7
Molding Shrinkage (3.2mm)	1.3 to 1.7	%	ASTM D9
Moisture Content	0.2		, to 1111 2 5
Molecular Controlle	0.2	70	
Mechanical Properties	Typical Value	Unit	Test Metho
Tensile Modulus	5597	MPa	ASTM D6
Tensile Strength	77.1	MPa	ASTM D6
Tensile Elongation(Yield)	3 to 3.9	%	ASTM D6
Flexural Modulus	4801	MPa	ASTM D7
Flexural Strength	129.7	MPa	ASTM D7
Impact Properties	Typical Value	Unit	Test Metho
Notched Izod Impact (3.2mm)	36.3	J/m	ASTM D2
Unnotched Izod Impact (3.2mm)	247	J/m	ASTM D48
ermeteries izes impast (eizimi)		37111	7.6111.2.10
Flammability	Typical Value	Unit	Test Metho
Ignition Resistance ¹	Typiour value	Office	
Flammability (1.5mm)	HB		ASTM D38
Hammability (1.5mm)			
Thermal Properties	Typical Value	Unit	Test Metho
Deflection Temperature Under Load	Typical value	Onit	rest Metric
1.8MPa Unannealed	116	$^{\circ}\!\mathbb{C}$	ASTM D6
T.OIVIFA OHAHHEARU			
Processing Information	Typical Value	I Init	
Processing Information Injection Pressure	Typical Value 70 to 125	MPa	
Melt Temperature	275 to 301		
		°C	
Mold Temperature	65 to 108	°C	
Drying Temperature	79	°C	
Drying Time	4	hr	
Dew Point	-18	$^{\circ}$	

Notes: Desiccant Type Dryer Required.

¹This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

NFD ADVANCED COMPOSITES

Hepla® H7240GB

CAUTION/警告!

Before using, read the Molding Guide, Material Safety Data Sheets, and Bulletins available from NFD Advanced Composites Sales offices and Distributors supplied to your company. Caution! During drying, purging and molding, small amounts of hazardous gases and/or particulate matter may be released. These may irritate eyes, nose and throat. Use adequate local exhaust ventilation during thermal processing. To prevent resin decomposition, do not contaminate the resin or exceed the recommended melt temperature or hold-up time. Avoid inhalation or skin and eyes contact. Sweep up and dispose of spilled resin to eliminate slipping hazard. 在使用之前,请阅读NFD公司销售办事处和经销商提供给贵公司的材料成型指南 、材料安全数据表和公告。警告! 在干燥、吹扫和成型过程中,少量有害气体或颗粒物质可能会在被释放,这些可能会刺激眼睛,鼻子和喉咙。热处理过程中请注意做好排气通风工作。为防止树脂分解,请勿污染树脂或超过我们为您推荐的熔融温度或时间。请避免吸入或与皮肤、眼睛等接触。清扫和处理溢出的树脂,以消除滑到的危险。

LEGAL NOTICES/法律声明

The figures indicated here are approximate values. They may be affected by different factors, and the user is not released therefore from the obligation of performing checks and trials of his own. The values indicated here have been compiled on the basis of current tests and findings. Any legally binding guarantee of certain properties, or any suitability for a specific application can not be inferred from the present data. For detailed production regulatory information, contact customer service.

上列数据只作参考用途,它们可能会受不同因素的影响,使用者有责任通过实验自行确定材料特性。上述资料根据现有测试得出,对物料特性是否适合某特殊用 途及特性不能给予保证,数据也没有任何法律约束力。更多有关详细的产品监管信息,请联系客户服务

COMPANY/公司:

Welcome to NFD, where the concept of "New Formula Designer" is upheld and scientific innovation and production are intertwined. Whether you are a designer, engineer or procurement expert, we can help you expand your business and get new inspiration. We adhere to the core values of credibility and integrity, cooperation, efficiency, and innovation, and always put our customers first. Compared with our competitors, we focus on providing more advanced technical formulation, better quality products, more efficient solutions and more thoughtful after-sales services. We understand the markets, the products, and you even more.

CONTACT:

CHINA/JIANG SU 江苏新孚达复合材料有限公司 NFD Composite Material (Jiangsu) Co., Ltd Email:yanghui@nfdpla.com Internet:www.nfdpla.com

