

Matreial Data Sheet

技术数据表

NFD Composite Material (Jiangsu) Co., Ltd

Tepla® T7210CF

Material Description:

Tepla ® T7210CF is a Polyetherketoneketone (PEKK) product filled with 10% carbon fiber. Characteristics include: High Heat Resistance.

General			
Material Status	Commercial: Active		
	Asia Pacific	North America	
Availability	• Europe	 Latin America 	
	Middle East	 Africa 	
Filler/Reinforcement	 Carbon Fiber, 10% Filler by 	Weight	
Features	High Heat Resistance	 High Strength 	
RoHS Compliance	 Contact Manufacturer 		
Appearance	Natural Color		
Forms	• Pellets		
Processing Method	Injection Molding		
Physical Properties	Typical Value		Test Method
Density/Specific Gravity		g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.10 to 0.30	%	ASTM D955
Water Absorption(24 hr, 23℃)	0.18	%	ASTM D570
Hardness	Typical Value	Unit	Test Method
Rockwell Hardness (R-Scale)	125	O I II C	ASTM D785
Nockwell Hardriess (N. Scale)	120		7101111 12700
Mechanical Properties	Typical Value	Unit	Test Method
Tensile Modulus	14300	MPa	ASTM D638
Tensile Strength (Yield)	172	MPa	ASTM D638
Tensile Elongation (Break)	2.2	%	ASTM D638
Flexural Modulus	10500	MPa	ASTM D790
Flexural Strength (Yield)	250	MPa	ASTM D790
Compressive Strength	210	MPa	ASTM D695
Impact Properties	Typical Value		Test Method
Notched Izod Impact(3.18 mm)	55	J/m	ASTM D256
Unnotched Izod Impact(3.18 mm)	652	J/m	ASTM D4812
Flammability	Typical Value	Unit	Test Method
Flame Rating	V-0	One	UL94
- Tomas Training	· •		5_0.
Electrical Properties	Typical Value	Unit	Test Method
Volume Resistivity	1.00E+08	ohms∙cm	ASTM D257
TI		11.50	T
Thermal Properties	Typical Value	Unit	Test Method
Deflection Temperature Unde Load	238	${\mathbb C}$	ASTM D648
1.8 MPa, Unannealed Glass Transition Temperature	156	${\mathbb C}$	ASTM E1356
Glass Transition Temperature	130	C	7.01111 [1000]
Injection	Typical Value	Unit	
Rear Temperature	357 to 399	$^{\circ}$ C	
Middle Temperature	357 to 399	$^{\circ}$ C	
Front Temperature	357 to 399	$^{\circ}$ C	
Mold Temperature	204 to 232	$^{\circ}$ C	
Injection Pressure	68.9 to 138	MPa	

NFD ADVANCED COMPOSITES

Tepla® T7210CF

CAUTION/警告!

Before using, read the Molding Guide, Material Safety Data Sheets, and Bulletins available from NFD Advanced Composites Sales offices and Distributors supplied to your company. Caution! During drying, purging and molding, small amounts of hazardous gases and/or particulate matter may be released. These may irritate eyes, nose and throat. Use adequate local exhaust ventilation during thermal processing. To prevent resin decomposition, do not contaminate the resin or exceed the recommended melt temperature or hold-up time. Avoid inhalation or skin and eyes contact. Sweep up and dispose of spilled resin to eliminate slipping hazard. 在使用之前,请阅读NFD公司销售办事处和经销商提供给贵公司的材料成型指南、材料安全数据表和公告。警告! 在干燥、吹扫和成型过程中,少量有害气体或颗粒物质可能会在被释放,这些可能会刺激眼睛,鼻子和喉咙。热处理过程中请注意做好排气通风工作。为防止树脂分解,请勿污染树脂或超过我们为您推荐的熔融温度或时间。请避免吸入或与皮肤、眼睛等接触。清扫和处理溢出的树脂,以消除滑到的危险。

LEGAL NOTICES/法律声明

The figures indicated here are approximate values. They may be affected by different factors, and the user is not released therefore from the obligation of performing checks and trials of his own. The values indicated here have been compiled on the basis of current tests and findings. Any legally binding guarantee of certain properties, or any suitability for a specific application can not be inferred from the present data. For detailed production regulatory information, contact customer service.

上列数据只作参考用途,它们可能会受不同因素的影响,使用者有责任通过实验自行确定材料特性。上述资料根据现有测试得出,对物料特性是否适合某特殊用途及特性不能给予保证,数据也没有任何法律约束力。更多有关详细的产品监管信息,请联系客户服务

COMPANY/公司:

Welcome to NFD, where the concept of "New Formula Designer" is upheld and scientific innovation and production are intertwined. Whether you are a designer, engineer or procurement expert, we can help you expand your business and get new inspiration. We adhere to the core values of credibility and integrity, cooperation, efficiency, and innovation, and always put our customers first. Compared with our competitors, we focus on providing more advanced technical formulation, better quality products, more efficient solutions and more thoughtful after-sales services. We understand the markets, the products, and you even

CONTACT:

CHINA/JIANG SU 江苏新孚达复合材料有限公司 NFD Composite Material (Jiangsu) Co., Ltd Email:yanghui@nfdpla.com Internet:www.nfdpla.com

