

**Matreial Data Sheet** 

技术数据表 NFD Composite Material (Jiangsu) Co., Ltd

# Tepla® T8210GF 5TF

## Material Description:

Tepla ® T8210GF 5TF is a Thermoplastic Polyimide (TPI) product filled with 10% glass fiber and 5% PTFE.Characteristics include:Lubricated.

include:Lubricated.			<u> </u>	
General				
Material Status	Commercial: Active			
	Asia Pacific		North America	
Availability	• Europe		Latin America	
	Middle East		Africa	
Filler/Reinforcement	Glass Fiber, 10% Filler by W	/eiaht	7 111100	
Additive	• PTFE Lubricant:5%	roigite		
, talaitive	High Strength		High Rigidity	
	Creep Resistant		Heat Resistant	
	Wear Resistant		Low Temperature Resistant	
Features	Electrical Insulation		Flame Retardant	
	Chemical Resistant		Good Dimensional Stability	
	Lubricated		Good Differisional Stability	
RoHS Compliance	RoHS Compliant			
Processing Method	Injection Molding			
Trocessing Method	- Injection Molaing			
Physical Properties	Typical Value		Test Method	
Specific Gravity	1.4	g/cm <sup>3</sup>	ASTM D792	
Molding Shrinkage (3.2mm)	0.4 to 0.7	%	ASTM D955	
Moisture Content	0.01	%		
Mechanical Properties	Typical Value	Unit	Test Method	
Tensile Modulus	5500		ASTM D638	
Tensile Strength	122	MPa	ASTM D638	
Tensile Elongation	4 to 6	%	ASTM D638	
Flexural Modulus	4800		ASTM D790	
Flexural Strength	176	MPa	ASTM D790	
Impact Properties	Typical Value	Unit	Test Method	
Notched Izod Impact (3.2mm)		J/m	ASTM D256	
Unnotched Izod Impact (3.2mm)	915	J/m	ASTM D4812	
Flammability	Typical Value	Unit	Test Method	
Ignition Resistance <sup>1</sup>	V/ 0		ACTA D2001	
Flammability (1.5mm)	V-0		ASTM D3801	
Electrical Properties	Typical Value	Unit	Test Method	
Volume Resistivity	>1E14	ohms•cm	ASTM D257	
Thermal Properties	Typical Value	Unit	Test Method	
Deflection Temperature Under Load 1.8MPa	>288	${\mathbb C}$	ASTM D648	
Processing Information	Typical Value	Unit		
Injection Pressure	138 to 194	MPa		
Melt Temperature	400 to 416	℃		
Mold Temperature	178 to 232	$^{\circ}$		
Drying Temperature	204			
Drying Time	6	hr		
,	Ŭ			

Moisture Content	0.01 %	
Dew Point	-40 °C	

Notes: Desiccant Type Dryer Required.

## NFD ADVANCED COMPOSITES

Tepla® T8210GF 5TF

#### CAUTION/警告!

Before using, read the Molding Guide, Material Safety Data Sheets, and Bulletins available from NFD Advanced Composites Sales offices and Distributors supplied to your company. Caution! During drying, purging and molding, small amounts of hazardous gases and/or particulate matter may be released. These may irritate eyes, nose and throat. Use adequate local exhaust ventilation during thermal processing. To prevent resin decomposition, do not contaminate the resin or exceed the recommended melt temperature or hold-up time. Avoid inhalation or skin and eyes contact. Sweep up and dispose of spilled resin to eliminate slipping hazard. 在使用之前,请阅读NFD公司销售办事处和经销商提供给贵公司的材料成型指南、材料安全数据表和公告。警告!在干燥、吹扫和成型过程中,少量有害气体或颗粒物质可能会在被释放,这些可能会刺激眼睛,鼻子和喉咙。热处理过程中请注意做好排气通风工作。为防止树脂分解,请勿污染树脂或超过我们为您推荐的熔融温度或时间。请避免吸入或与皮肤、眼睛等接触。清扫和处理溢出的树脂,以消除滑到的危险。

#### LEGAL NOTICES/法律声明

The figures indicated here are approximate values. They may be affected by different factors, and the user is not released therefore from the obligation of performing checks and trials of his own. The values indicated here have been compiled on the basis of current tests and findings. Any legally binding guarantee of certain properties, or any suitability for a specific application can not be inferred from the present data. For detailed production regulatory information, contact customer service

上列数据只作参考用途,它们可能会受不同因素的影响,使用者有责任通过实验自行确定材料特性 。上述资料根据现有测试得出,对物料特性是否适合某特殊用 途及特性不能给予保证,数据也没有任何法律约束力。更多有关详细的产品监管信息,请联系客户服务。

#### COMPANY/公司:

Welcome to NFD, where the concept of "New Formula Designer" is upheld and scientific innovation and production are intertwined. Whether you are a designer, engineer or procurement expert, we can help you expand your business and get new inspiration. We adhere to the core values of credibility and integrity, cooperation, efficiency, and innovation, and always put our customers first. Compared with our competitors, we focus on providing more advanced technical formulation, better quality products, more efficient solutions and more thoughtful after-sales services. We understand the markets, the products, and you even more.

Moles Mac Manager Man

### CONTACT:

CHINA/JIANG SU 江苏新孚达复合材料有限公司 NFD Composite Material (Jiangsu) Co., Ltd Email:yanghui@nfdpla.com Internet:www.nfdpla.com



<sup>&</sup>lt;sup>1</sup>This rating is not intended to reflect hazards of this or any other material under actual fire conditions.